



## TECHNICAL DATA SHEET

### CPE Shoe Covers

Item Series 2308CPE-SB



#### Fabric Features

- **Light-weight CPE film construction** – provides protection against dust and light splash.
- **Low-linting, latex-free,** and fire-retardant.

#### Design & Application

- **Heat-sealed seams** prevent water leakage.
- **Disposable** and cost-effective.
- **Suitable for use** in hospitals, clinics, and animal research facilities.

#### Specifications

|           |                |
|-----------|----------------|
| Color     | Blue           |
| Sizes     | Regular and XL |
| Packaging | 300 pcs / case |

#### Item Codes

| Size    | Item Code    |
|---------|--------------|
| Regular | 2308CPE-SBR  |
| XL      | 2308CPE-SBXL |

#### Measurements

| Size    | Length | Height |
|---------|--------|--------|
| Regular | 16.5"  | 6.5"   |
| XL      | 17.5"  | 6.5"   |



## Fabric Properties & Performance Data

---

*Embossed CPE film.*

| Property                      | Test Method | Value    |
|-------------------------------|-------------|----------|
| <b>Fabric Type</b>            | —           | CPE Film |
| <b>Thickness</b>              | ASTM D6988  | 2 mil    |
| <b>Break Force (MD)</b>       | ASTM D882   | 18 N     |
| <b>Tensile Strength (CD)</b>  | ASTM D882   | 15 N     |
| <b>Elongation (MD)</b>        | ASTM D882   | 350%     |
| <b>Elongation (CD)</b>        | ASTM D882   | 400%     |
| <b>Blood Penetration Test</b> | ASTM F1670  | Pass     |
| <b>Viral Penetration Test</b> | ASTM F1671  | Pass     |
| <b>Flammability</b>           | 16 CFR 1610 | Class 1  |

## Customer Service

---

**Tel:** 610-295-9033

**Email:** [orders@apexaseptic.net](mailto:orders@apexaseptic.net)

---

*The information contained in this Technical Data Sheet is provided in good faith and believed to be accurate at the time of publication. Values are typical and not intended for use as specification limits. It is the user's responsibility to determine the suitability of this product for its intended application. Apex Aseptic Products, Inc. makes no warranty, expressed or implied, regarding the accuracy of this data or the results obtained from its use.*